



## WHITECHEM PRIMER M80

### 1 – PRODUCT DESCRIPTION

**WHITECHEM PRIMER M80** is a two component, epoxy based primer with excellent corrosion protection properties for use on metal surfaces. It has high structural strength, abrasion and chemical resistance.

### 2 – FEATURES

- Excellent adhesion to metal surfaces
- Protect metal from corrosion
- Resistant to acids, bases, oils, gasoline, solvents and salt water
- Perfect resistance to water, freeze, humidity and harsh weather conditions
- Easy application
- Can be used indoor and outdoor applications
- Long working time and pot life

### 3 – APPLICATION AREAS

- Whitechem Primer M80 designed as an anticorrosive & anti-rusting primer on iron and steel substrates prior to the application of waterproofing membranes and coatings.
- Application examples include protection of silos, steel bridges, fences, metals roofs, pipes, reinforcement bars etc.

### 4 – SURFACE PREPERATION AND APPLICATION

**Substrate:** All substrates must be structurally sound, clean and dry and free from oil, grease and loose material and any other contamination that might impair adhesion. According to the nature of the substrate, it should be prepared by brushing, grinding, sand blasting, etc. Following this, the surface should be cleaned from dust. Application of primer must be completed before an oxide layer is able to form.

**Mixing of the components:** Components A (resin) and B (hardener) are packed in two separate containers, having the correct predetermined mixing proportion by weight. The whole quantity of component B is added into component A. Mixing of the 2 components should take place for about 5 minutes, using a low revolution mixer (300 rpm). It is important to stir the mixture thoroughly near the sides and bottom of the container, to succeed uniform dispersion of the hardener. Keep the mixing head submerged to avoid entrapping air.

**Application:** It is applied in one or two coats by roller, brush or spray. The second layer follows after the first has dried, but within 24 hours.



## 5- PACKAGING

24 kg set

A (resin): 20 kg and B (hardener): 4 kg

## 6- SHELF LIFE & STORAGE

12 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.

## 7- SAFETY

For information and precautions on the safe handling, transportation storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## 8- TECHNICAL FEATURES

Basis	: Two Component Epoxy Resin
Appearance/Color	: Colorless, blurry
Density (A+B)	: 1,47 gr/cm <sup>3</sup>
Viscosity (A+B)	: 480 cps ( 25 °C)
Open time	: 2 hours (23 °C 50 % R.H.)
Light foot traffic	: 12-18 hours (23°C 50% R.H.)
Full cure time	: 7 days (23 °C 50 % R.H.)
Min. cure temperature	: +8°C
Application temperature	: +15 °C and +30 °C
Consumption	: 0,3-0,5 kg/m <sup>2</sup> /layer
Recoat time	: 3-24 hours
Shore A Hardness	: 95
Adhesion force (steel)	: > 3 N/mm <sup>2</sup>
Corrosion protection	: Pass ( 2000 hours, ASTM B-117)

## 9-LEGAL NOTICE

The information presented herein is given in good faith but without warranty. It's based on our experience, indicates our laboratory work results and does not necessarily indicate final product performance. We cannot be held liable for the results obtained with our products and for any loss or accident that may result from its use. Our suggestions don't release you from the obligation to check their validity and to test our products for both your process and end use application. All our products are sold in accordance with our General Conditions of Sale. We don't make any warranty, express or implied, including but not limited to the merchantability and fitness for a particular purpose.